

### AMENDMENTS TO THE CLAIMS

**Claim 1 (Currently Amended)** A copper-clad laminate of a glass fabric/thermosetting resin base material, which is used to form a small-diameter hole with a carbon dioxide gas laser, formed of prepreg obtained by impregnating a glass fabric base material made of a glass woven fabric having a thickness of 25 to 150  $\mu\text{m}$ , a weight of 15 to 165  $\text{g/m}^2$  and a gas permeability of 1 to 20  $\text{cm}^3/\text{cm}^2/\text{sec.}$ , with a thermosetting resin composition being dissolved in a solvent and drying it.

2. **(Previously Added)** The copper-clad laminate according to claim 1, wherein the thermosetting resin composition in the copper-clad laminate contains an insulating inorganic filler in an amount of 10 to 80 % by weight based on the above resin composition.

3. **(Previously Added)** The copper-clad laminate according to claim 1, wherein the prepreg has a glass content of 25 to 70 % by weight.

4. **(Previously Added)** The copper-clad laminate according to claim 1, wherein a glass fabric/thermosetting resin base material layer of the copper-clad laminate has a thickness of 30 to 150  $\mu\text{m}$ .

5. **(Previously Added)** The copper-clad laminate according to claim 1, wherein the thermosetting resin composition is a resin composition containing, as an essential component, a polyfunctional cyanate ester and a prepolymer of said polyfunctional cyanate ester.